



**MULFORD**  
PLASTICS  
*delivering solutions*

**PETG**

## Vipet® PETG

Vipet PETG is a versatile co-polyester sheet used for a wide range of applications that require exceptional clarity and mechanical properties. Vipet PETG is an ideal product for vacuum formed process for point of sale parts due to not having to pre-dry the material. PETG has the ability to reposition and reform, and the ability to down gauge some individual parts to due to a higher impact strength than that of PMMA. Vipet PETG therefore offers designers a high degree of freedom for realizing intricate transparent shapes and fast becoming an environmentally viable alternative to clear PVC.

### Key Features

- Excellent thermoforming characteristics
- High impact strength
- Easily die cut and punched
- Cost effective
- Printable
- High optical quality

### Product Applications

- Merchandising/Point of sale displays
- Vending Machines
- Product Dispensers
- Medical Packaging
- Food Storage/displays
- Industrial guards and covers
- Slatt wall components

## TECHNICAL DATA SHEET

<b>GENERAL</b> Density Water Absorption	ISO1183 ISO62	1.27 (0.0458) 0.3	g/cm <sup>3</sup> (lb/in <sup>3</sup> ) %
<b>MECHANICAL</b> Tensile Strength Elongation at Break Tensile Modulus Flexural Strength Flexural Modulus Izod Impact Strength, Notched, 23°C Izod Impact Strength, Notched, -30°C	ISO527-2 ISO527-2 ISO527-2 ISO178 ISO178 ISO179-1 ISO180/1A	50 (7252) 54 2050 (297316) 70 (10152) 2050 (297316) 7 (3.33) 7 (3.33)	MPa (psi) % MPa (psi) MPa (psi) MPa (psi) kJ/m <sup>2</sup> (ft-lb/in <sup>2</sup> ) kJ/m <sup>2</sup> (ft-lb/in <sup>2</sup> )
<b>THERMAL</b> Vicat Softening Temperature, B50, Annealed Heat Distortion Temperature, 1.8MPa Linear Thermal Expansion Continuous Service Temperature Maximum Short Term Temperature Degradation Temperature	ISO306 ISO75 DIN53752 - - -	79 (174) 64 (147) 7 55 (131) 65 (149) > 250 (> 482)	°C (°F) °C (°F) /°K x 10-5 °C (°F) °C (°F) °C (°F)
<b>OPTICAL</b> Light Transmission (3mm / 0.118") Refractive Index	DIN5036-3 DIN5036-3	87 1.57	% -----
<p>This specification provides typical data to the best of our knowledge at the time of publishing. Due to our inability to control conditions of use and application, we are unable to make any recommendations or suggestions. Mulford International nor any of their suppliers assume any liability for use of information presented.</p>			

☎ **AUST** 1300 MULFORD (1300 6853673) **NZ** 0800 MULFORD (0800 6853673)

📍 **AUST** Brisbane | Newcastle | Sydney | Melbourne | Adelaide | Perth

**NZ** Auckland | Hamilton | Wellington | Christchurch

👉 **WWW.MULFORDPLASTICS.COM**